

試驗報告



報告編號：HV-3-05273X

頁數：1 OF 1

報告日期：102年08月27日

委託單位：科定企業股份有限公司
 地址：新北市泰山區中山路二段431巷16號
 樣品名稱：科定塗裝木皮板
 送驗人員：科定企業股份有限公司(紀權真)
 收件日期：102年08月13日
 試驗日期：102年08月13日~102年08月26日
 備註：以上資料由顧客提供(收件及試驗日期除外)

試驗結果：

試驗項目	試驗方法	試驗結果
耐光性(WV type, 48小時) 色差 ΔE^*	CNS 11367(1985)	外觀無龜裂、剝離現象 0.7

註：1.本試驗報告耐光性委託 SGS 材料及工程實驗室-高雄執行。

2.試驗機型式：SUGA U-48

濾鏡：密閉式

使用光源：Ultraviolet Carbon Arc

測試條件：
 黑板溫度：63±3°C
 試驗槽溫度：42±3°C
 相對濕度：30±5%RH
 測試週期：100%照光

----- o O o -----

規範要求值僅供參考，合格之判定以委託單位實際要求為準。

高偉閔
 報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.